

CAMEL EMULSION PAINT CC-SERIES

Product Introduction

RECOMMENDED USES	:	Suitable for plastered interior cementitious walls.
DESCRIPTION	:	<p>CC-Line is a high quality durable paint for the protection of interior wall surfaces. It is easy to apply paint with excellent hiding power and film build. It dries quickly to form a hardwearing, mould inhibitive film with long-lasting appearance. It is highly recommended by professional decorators.</p> <ul style="list-style-type: none"> ● Excellent interior durability ● Fungus Resistant ● High Opacity ● Resisting to Fading ● Ease of Application ● No unpleasant Odor
STANDARD PACKING	:	1 liter, 4 liters & 18 litres.

Technical Data

BASE RESIN	:	Acrylic / Acetate copolymer
COLOR	:	As per color card, BS5252F:1976, Tailor-made colors on request
PRODUCT STANDARD	:	GB 9756-2009 GB 18582-2008
VOLUME SOLIDS	:	Approx. 40% (values may vary with colors)
FINISH	:	Matt
TOXICITY CONTROL	:	No added Lead, Mercury, Chromium and Cadmium. VOC < 100g/l, according to ASTM D3960-96.
CALCULATED COVERAGE	:	Approx. 20 sq.m / ltr @ 25 Microns DFT depends on surface condition and wastage
RECOMMENDED FILM THICKNESS PER COAT	:	Wet : 50 –63 microns Dry : 20-25 microns
DRYING TIME	:	
Touch Dry	:	1 hour
Hard Dry	:	2 hours
Over coating @20°C	:	
Minimum	:	3 hours
Maximum	:	-Indef.

Notes: Product data is based on in-house testing methods modified from BS3900/ASTM.
Content will be updated without prior notice.
Surface preparation, application method and condition will affect product performance. We are not responsible for the performance, unless agreed in writing by us.

Technical Bulletin No.CC/1002/B/10

Page 1 of 2

CAMEL EMULSION PAINT CC-SERIES

Application

RECOMMENDED THINNER	:	Water
CLEANING SOLVENT	:	Water
RECOMMENDED SEALER	:	Camel Alkali Resistant wall Sealer MA473
METHOD OF APPLICATION	:	
Recommended coats	:	2 coats
By Brush	:	Dilute 10 parts of paint with 3 parts of water by volume.
By Roller	:	Dilute 10 parts of paint with 2 parts of water by volume.
By airless spray	:	Dilute 10 parts of paint with 2 parts of water by volume.
By conventional spray	:	Dilute 10 parts of paint with 4 parts of water by volume.
Painting is recommended to carry out on fine day.		
Surfaces to be coated must be sound, clean, non-dusting, free from oil, grease, moisture and foreign particles. For recoating old surfaces, all chalked and scaled materials must be removed before painting.		
Stir the paint well before use.		

Safety Precaution

DANGEROUS GOODS CLASSIFICATION	:	Not applicable.
SHELF-LIFE	:	36 Months.
APPLICATION CONDITIONS	:	Maintain temperature in areas to receive coatings at minimum 7 deg. C, during application and until coatings have cured.
	:	Adequately ventilate areas where coatings are being applied.
	:	Maintain a reasonably dust-free atmosphere for duration of work.
	:	Protect adjacent surfaces not scheduled to receive coatings from damage and overcoat.
	:	Post "Wet Coating" signs while work is in progress and while coatings are curing.
OTHER CONSIDERATIONS	:	Material to be delivered and stored in undamaged, original manufacturers' containers.
	:	Keep container closed when not in use.
	:	Stir the paint well before use.
	:	Store at cool, dry place.
HEALTH & SAFETY PRECAUTIONS	:	Ingestion : Send the affected person to hospital or obtain medical attention immediately. Do not induce vomiting.
	:	Skin contact : Flush immediately with water and remove contaminated clothing. Use soap if available. If irritation persists refer for medical attention.
	:	Eye contact : Flush immediately with water and get medical care.
	:	Inhalation : Remove the affected person to fresh air and obtain medical attention if rapid recovery does not occur.
REGULATED PRODUCT CODE	:	Flat Coatings P09-02
VOC CONTENT	:	≤ 50g/ltr

Notes: Product data is based on in-house testing methods modified from BS3900/ASTM.
Content will be updated without prior notice.
Surface preparation, application method and condition will affect product performance. We are not responsible for the performance, unless agreed in writing by us.